

B 11



(19)

(11) Publication number: **200**

Generated Document.

**PATENT ABSTRACTS OF JAPAN**(21) Application number: **2000266018**(51) Intl. Cl.: **B65D 65/02 B65D 41/00 C08  
23/10 C08L 53/00**(22) Application date: **01.09.00**

<p>(30) Priority:</p> <p>(43) Date of application publication: <b>08.03.02</b></p> <p>(84) Designated contracting states:</p>	<p>(71) Applicant: <b>JAPAN CROWN CORK</b></p> <p>(72) Inventor: <b>YOSHIMOTO MITSUNO MATSUDA GUNJI SUZUKI NOBORU KIKUCHI HIROAKI KANANO YUJI</b></p> <p>(74) Representative:</p>
---	---

**(54) CAP MADE OF RESIN  
WHICH CAN BE HEAT-  
STERILIZED**

(57) Abstract:

**PROBLEM TO BE SOLVED:** To provide an easily openable cap made of a resin which has heat-resistance to withstand a heat-sterilization such as a hot filling, and at the same time, wherein a cap opening torque can be suppressed to a low value by a small using amount of a lubricant, and a combination of sealability, cap opening property and mechanical strength or the like is excellent.

**SOLUTION:** This heat-sterilizable cap made of the resin is formed of a resin composition which contains a propylene based polymer and a high density polyethylene with an amount ratio wherein the high density polyethylene becomes 2 to 10 pts.wt. based on 100 pts.wt. of the propylene

copolymer. In this case, for the propylene based polymer, the melt flow rate (at a temperature of 230°C, and a load of 21.18 N) is 3 to 20 g/10 min. For the high density polyethylene, the melt flow rate (at a temperature 190°C, and a load of 21.18 N), is 1 to 20 g/10 min, and the density is 0.940 to 0.970 g/cm<sup>3</sup>. Also, the resin composition contains the lubricant of 0.3 to 1.0 wt.% per resin.

COPYRIGHT: (C)2002,JPO

